

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
6 June 2002 (06.06.2002)

PCT

(10) International Publication Number
WO 02/44220 A1

- (51) International Patent Classification⁷: **C08F 4/654**, 10/00 (74) Agents: **DEPENNING, Robert, G.** et al.; DePenning & DePenning, Alaknanda, 16 Nepean Sea Road, Mumbai 400 036, Maharashtra (IN).
- (21) International Application Number: PCT/IN00/00114
- (22) International Filing Date:
29 November 2000 (29.11.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (71) Applicant (for all designated States except US): **RELIANCE INDUSTRIES LIMITED** [IN/IN]; 5th Floor, Maker Chambers IV, 222, Nariman Point, Mumbai 400 021, Maharashtra (IN).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **BHADURI, Sumit** [IN/IN]; Reliance Industries Limited, Swastik Mills Compound, Sion-Trombay Road, VN Purav Marg, Chembur, Mumbai 400 071, Maharashtra (IN). **GUPTA, Virendra, Kumar** [IN/IN]; Reliance Industries Limited, Swastik Mills Compound, Sion-Trombay Road, VN Purav Marg, Chembur, Mumbai 400 071, Maharashtra (IN).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 02/44220 A1

(54) Title: A LOWER α -ALKENE POLYMERISATION HETEROGENEOUS SOLID CATALYST

(57) Abstract: A lower α -alkene polymerisation heterogeneous solid catalyst which comprises a hydrated magnesium chloride derived procatalyst, a cocatalyst comprising an organoaluminium compound and a selectivity control agent comprising an ester or ether. The procatalyst comprises a titanium tetrahalide supported on a magnesium chloride ester complex precursor. The procatalyst is obtained by refluxing hydrated magnesium chloride with an aliphatic alcohol in a hydrocarbon and/or haloalkane solvent followed by dehydration of the reaction mixture. The magnesium chloride alcoholate is reacted with an activated carbonyl compound in the presence of a hydrocarbon and/or haloalkane solvent optionally followed by dehydration of the reaction mixture. The precursor is reacted with a titanium tetrahalide optionally in the presence of a hydrocarbon and/or haloalkane solvent at 30/130°C followed by isolating the resulting procatalyst.

TITLE OF INVENTION

A LOWER α -ALKENE POLYMERISATION HETEROGENEOUS SOLID CATALYST

This invention also relates to a process for the preparation of the heterogeneous solid catalyst and a process for the polymerisation of a lower α -alkene using the heterogeneous solid catalyst.

Background Art

Polymers of lower α -alkenes or olefins such as ethylene, propylene or 1-butene find applications in the manufacture of a variety of articles including plastic bags or sheets or automobile parts. Of particular interest in polymer production is polypropylene with a high degree of isotacticity i.e. the extent of orientation of the branched groups in the polymer in the same direction, which shows high crystallinity. The polymerisation involves reacting the lower α -alkene such as propylene with a catalyst under polymerisation conditions. The early polymerisation catalysts were of relatively low activity and the polymers formed contained significant amounts of the catalyst residues which had to be removed by deashing steps. The more recent alkene polymerisation catalysts are of two types viz. the single site catalysts and the heterogeneous solid catalysts. The single site catalysts comprise metallocenes or co-ordination complexes of transition metals and a cocatalyst such as methyl alumino oxane. These catalysts show activity when used in solution.

Heterogeneous solid catalysts are the most commonly used catalysts, specially in the bulk production of polyethylene or polypropylene, due to their high activity. A heterogeneous solid catalyst comprises a procatalyst, a cocatalyst and a selectivity control agent. The cocatalyst may be an organoaluminium compound such as alkyl aluminium. The selectivity control agent may be an ester such as p-substituted benzoate or phthalate ester or an ether such as alkyl, alkoxy or aryl alkoxy silane. The physicochemical properties of the procatalyst plays a pivotal role in the overall performance of the catalyst, particularly in producing polymers of high isotacticity index. The procatalysts are synthesised by halogenation of an organomagnesium compound such as magnesium ethoxide with a halogenating agent such as titanium tetrahalide in a hydrocarbon or halo hydrocarbon solvent such as toluene or chlorobenzene to form magnesium chloride. The magnesium chloride so obtained is reacted with titanium alkoxide or excess titanium tetrahalide, usually titanium tetrachloride in the presence of a hydrocarbon/halo hydrocarbon solvent. To this an internal electron donor such as an ester, for example ethyl benzoate, is added simultaneously or sequentially to result in a procatalyst. (US Patents Nos 4535068, 4414132, 4400302, 4477639, 4497905, 4535068, 4657995, 4710482, 4728705, 4771024, 4804648, 4870039, 4914069, 4870040, 5066737, 5077357, 5106806, 5082907, 5122494, 5124298, 5141910, 5151399 and 5229342). In most of the above processes employing organomagnesium compounds, halogenation is usually carried out with titanium tetrahalide itself, because of which these routes necessitate use of higher amounts of titanium reagents in the preparation of the procatalyst, thereby rendering these processes expensive. Besides, organomagnesium compounds such as magnesium alkoxides in the presence

of titanium compounds may result in by-products. Since an ester as such is separately added to the reaction mixture, there are chances of the free ester being present, which will react with the titanium tetrahalide ["Reactions of titanium tetrachloride with diesters", J Organomet. Chem. (1993), 443(1), 85 - 91 by Sobota Piotr et al; "Synthesis and crystal structure of the titanium tetrachloride-ethyl propionate adduct", Z Kristallogr. (1991), 194 (3 - 4), 267 - 72]. This reaction is exothermic and generates by-products in the preparation of the procatalyst which may affect the performance /activity of the catalyst.

Procatalysts may also be prepared by a method comprising milling together anhydrous magnesium chloride, a titanium tetrahalide such as titanium tetrachloride and an internal electron donor such as an ester in a hydrocarbon or halohydrocarbon solution at ambient temperature to produce a precursor. The precursor is then reacted with titanium tetrahalide to produce the procatalyst (US Patents Nos 4329253 and 4393182). In yet another method, anhydrous magnesium chloride is milled with an internal electron donor such as an ester to produce a precursor which is milled with titanium tetrahalide (US Patent No 4419501). Anhydrous magnesium chloride used in the above methods is expensive and not readily available. Procatalysts formed by these physical methods when used in polymerisation reactions, may show poor selectivity and result in polymers with low isotacticity index. In this process also by-products formation due to reaction of titanium tetrahalide with free ester cannot be negated. Due to use of anhydrous magnesium chloride, additional steps such as spray drying or melting may be required which render the process time consuming. Also the first method

demands use of large amounts of titanium reagent, firstly for halogenation of magnesium chloride and then for being supported on the precursor. The use of excess titanium reagent makes the process expensive.

5 US Patent No 4948770 describes a process for the preparation of a heterogeneous solid procatalyst comprising titanium compound such as titanium tetrahalide supported on a precursor obtained by reaction of magnesium halide alcoholate formed of anhydrous magnesium chloride and an aliphatic alcohol such as ethanol or isobutanol with anhydrous silica, and
10 an internal electron donor such as an ester.

US Patent No 4535068 describes a process for the preparation of a heterogeneous solid procatalyst comprising titanium tetrahalide supported on a precursor obtained by halogenation of an organomagnesium compound
15 such as magnesium diethoxide with titanium tetrahalide and an internal electron donor such as an ester in a halohydrocarbon solvent and reacting the resulting halogenated magnesium compound with an acid halide such as benzoyl chloride. Although not specifically stated in the above patent, addition of acid halide is expected to be for the removal of by-products
20 formed during the course of the reaction. In the above process also, since an ester is as such separately added to the reaction mixture containing titanium tetrahalide, there are chances of by-product formation by reaction of ester with titanium tetrahalide. Organomagnesium compounds in the presence of titanium tetrahalide may also result in by-products and affect the performance
25 of the catalyst. This route also employs a two-stage use of titanium reagent and is expensive.

Objects of invention

An object of the invention is to provide a lower α -alkene polymerisation heterogeneous solid catalyst comprising a hydrated magnesium chloride derived procatalyst which is less expensive.

Another object of the invention is to provide a lower α -alkene polymerisation heterogeneous solid catalyst which comprises a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor, wherein the internal electron donor ester component of the precursor is generated insitu.

Another object of the invention is to provide a lower α -alkene polymerisation heterogeneous solid catalyst comprising a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor, wherein the precursor of the procatalyst is synthesised without using an ester because of which generation of by-products is minimised.

Another object of the invention is to provide a lower α -alkene polymerisation heterogeneous solid catalyst comprising a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor, which when used in polymerisation shows high activity and selectivity and results in polymers with high isotacticity index.

Another object of the invention is to provide a process for the preparation of a lower α -alkene polymerisation heterogeneous solid catalyst

employs less expensive and readily available reagent viz. hydrated magnesium chloride as starting material.

Another object of the invention is to provide a process for the preparation of a lower α -alkene polymerisation heterogeneous solid catalyst which comprises a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor, wherein the internal electron donor ester component of the precursor is generated insitu.

Another object of the invention is to provide a process for the preparation of a lower α -alkene polymerisation heterogeneous solid catalyst comprising a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor, wherein the precursor of the procatalyst is synthesised without using an ester because of which generation of by-products is minimised.

Another object of the invention is to provide a process for the preparation of a lower α -alkene polymerisation heterogeneous solid catalyst comprising a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor, which is less time consuming.

Another object of the invention is to provide a process for the preparation of a lower α -alkene polymerisation heterogeneous solid catalyst comprising a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor, which when used in

polymerisation shows high activity and selectivity and results in polymers with high isotacticity index.

Another object of the invention is to provide a process for a lower α -alkene polymerisation using a heterogeneous solid catalyst comprising a hydrated magnesium chloride derived procatalyst which is less expensive.

Another object of the invention is to provide a process for a lower α -alkene polymerisation using a heterogeneous solid catalyst which comprises a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor, wherein the internal electron donor ester component of the precursor is generated insitu.

Another object of the invention is to provide a process for a lower α -alkene polymerisation using a heterogeneous solid catalyst comprising a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor wherein the precursor of the procatalyst is synthesised without using an ester because of which generation of by-products is minimised.

Another object of the invention is to provide a process for a lower α -alkene polymerisation using a heterogeneous solid catalyst comprising a titanium tetrahalide supported on a chemically bonded magnesium chloride ester complex precursor, which results in polymers with high isotacticity index.

According to the invention there is provided a lower α -alkene polymerisation heterogeneous solid catalyst comprising:

5 A) a hydrated magnesium chloride derived procatalyst comprising a titanium tetrahalide supported on a magnesium chloride ester complex precursor, wherein the internal electron donor ester component of the precursor is generated insitu by reaction of a magnesium chloride alcoholate with an activated carbonyl compound in the mole ratio 0.5 - 1 : 10 - 20; wherein the magnesium chloride alcoholate is formed of hydrated
10 magnesium chloride and an aliphatic alcohol in the mole ratio of 0.5 - 1 : 10 - 20;

B) a cocatalyst comprising an organoaluminium compound, the mole ratio of the aluminium to the titanium being 10 - 300 : 1; and
15

C) a selectivity control agent comprising an ester or ether in the mole ratio 10 - 100 : 1 with respect to the titanium.

20 According to the invention there is also provided a process for the preparation of a lower α -alkene polymerisation heterogeneous solid catalyst comprising mixing a hydrated magnesium chloride derived procatalyst, a cocatalyst comprising an organoaluminium compound and a selectivity control agent comprising an ester or ether, wherein the procatalyst is obtained by:

i) refluxing hydrated magnesium chloride with an aliphatic alcohol in the mole ratio 0.5 - 1 : 10 - 20 in a hydrocarbon and/or halohydrocarbon solvent followed by dehydration of the reaction mixture;

5 ii) reaction of the resulting magnesium chloride alcoholate with an activated carbonyl compound in the presence of a hydrocarbon and/or halohydrocarbon solvent in the mole ratio 0.5 - 1 : 10 - 20 at 30 - 160°C optionally followed by dehydration of the reaction mixture;

10 iii) reaction of the resulting magnesium chloride ester complex precursor comprising the internal electron donor ester component generated insitu, with a titanium tetrahalide optionally in the presence of a hydrocarbon and/or halohydrocarbon solvent at 30 - 130°C followed by isolating the resulting procatalyst; the mole ratio of the aluminium to the titanium being 10 - 300 : 1 and that of the selectivity control agent to the titanium being 10 - 100 : 1.

15 According to the invention there is also provided a process for a lower α -alkene polymerisation comprising reacting under polymerisation conditions a lower α -alkene with a heterogeneous solid catalyst comprising:

25 A) a hydrated magnesium chloride derived procatalyst comprising a titanium tetrahalide supported on a magnesium chloride ester complex precursor, wherein the internal electron donor ester component of the precursor is generated insitu by reaction of a magnesium chloride alcoholate with an activated carbonyl compound in the mole ratio 0.5 - 1 : 10 -

20; wherein the magnesium chloride alcoholate is formed of hydrated magnesium chloride and an aliphatic alcohol in the mole ratio of 0.5 - 1 : 10 - 20;

B) a cocatalyst comprising an organoaluminium compound, the mole ratio of the aluminium to the titanium being 10 - 300 : 1; and

C) a selectivity control agent comprising an ester or ether in the mole ratio 10 - 100 : 1 with respect to the titanium.

The lower α -alkenes used for polymerisation may be ethylene, propylene, 1-butene and/or 1-hexene to produce homopolymers or copolymers. Preferably propylene is used.

The heterogeneous solid procatalyst may have a surface area of 40 - 300 m²/g, preferably 50 - 200 m²/g.

The halide in the titanium tetrahalide may be chloride or bromide, preferably chloride.

Hydrated magnesium chloride used for reaction may be commercially available. The aliphatic alcohol used may be ethanol, propanol, n-butanol, iso-butanol, isopropanol or 2-ethyl hexanol to produce the corresponding magnesium chloride alcoholate. Preferably ethanol, n-butanol or iso-butanol is used. To produce the magnesium chloride alcoholate,

hydrated magnesium chloride and aliphatic alcohol are used preferably in the mole ratio 1 : 10.

5 The activated carbonyl compound may be that which generates a magnesium chloride ester complex on reaction with a magnesium chloride alcoholate. Preferably the activated carbonyl compound may be an acid halide such as benzoyl chloride, phthaloyl chloride or acetyl chloride, preferably benzoyl chloride or phthaloyl chloride. Alternatively the activated carbonyl compound may be an acid anhydride such as benzoic anhydride, phthalic anhydride or acetic anhydride, preferably benzoic anhydride or phthalic anhydride.

15 The reaction between the magnesium chloride alcoholate and the activated carbonyl compound may be carried out insitu or following isolation of the magnesium chloride alcoholate. This reaction is carried out preferably at 100 - 110°C. The mole ratio of the magnesium chloride alcoholate to the activated carbonyl compound is preferably 0.5 : 10. If the activated carbonyl compound used is an acid anhydride then the reaction mixture is dehydrated following reaction of the magnesium chloride alcoholate and the activated carbonyl compound. Dehydration of the reaction mixture is carried out preferably by azeotropic distillation.

25 The precursor is reacted with a titanium tetrahalide preferably at 90 - 120°C.

The hydrocarbon or halohydrocarbon solvent may be aliphatic or aromatic. The hydrocarbon may be toluene, xylene or decane. The halohydrocarbon may be chlorobenzene or dichlorobenzene. Preferably toluene and/or chlorobenzene is used.

The isolation of the procatalyst involves filtration, washing with a hydrocarbon solvent such as toluene and drying of the solid.

The organoaluminium cocatalyst may be trialkyl or mixed halo alkyl or alkoxo alkyl aluminium compounds usually employed with titanium procatalysts. These may be commercially available or prepared in known manner. Preferably triethyl aluminium is used.

Preferably the mole ratio of the aluminium in the cocatalyst to the titanium in the procatalyst of the catalyst is 200 : 1.

The selectivity control agent is an ester such as p-substituted benzoate or phthalate ester, preferably p-ethoxy ethyl benzoate or an ether such as alkyl alkoxy or aryl alkoxy silane usually employed with titanium procatalysts. Preferably dicyclohexyl dimethoxy silane or diphenyl dimethoxy silane is used. The selectivity control agents may be commercially available or prepared in known manner.

Preferably the mole ratio of the selectivity control agent to the titanium in the procatalyst in the catalyst is 10 - 75 : 1.

The components of the polymerisation catalyst viz. the procatalyst, cocatalyst and the selectivity control agent may be mixed in a vessel outside the polymerisation reactor before being transferred to the polymerisation reactor. Alternatively the components may be individually transferred into the polymerisation reactor to generate the active catalyst insitu.

The polymerisation may be conducted with one or more lower α -alkenes to produce homopolymers or copolymers, in the gas phase employing one or more fluidised beds of catalyst in known manner. Alternatively the polymerisation may also be conducted in the slurry phase in the absence or presence of an inert hydrocarbon diluent such as hexane in known manner.

According to the invention cheap and readily available hydrated magnesium chloride is used as starting material in the preparation of the procatalyst, instead of organomagnesium compounds or anhydrous magnesium chloride. Besides, during the course of the reaction of magnesium chloride alcoholate with the activated carbonyl compound, the internal electron donor ester component is generated insitu and that too as part of the magnesium chloride ester complex precursor. Therefore there is no free ester available for reaction with titanium tetrahalide and by-product formation is eliminated. Due to use of hydrated magnesium chloride, the process for the preparation of the procatalyst thus eliminates additional steps such as spray drying or melting or use of halogenating agents and consumes titanium reagents only at a single stage in the process for the preparation of the procatalyst. Therefore less amounts of titanium reagents are consumed. This makes the process less expensive and less time consuming. Since the

procatalyst is not formed using organomagnesium compounds, further by-products formation is eliminated. The procatalyst prepared by the process of the invention is a chemically bonded one and not a physical mixture of its ingredients. The procatalyst prepared by the process of the invention shows high activity and selectivity, particularly in producing polymers with high isotacticity index.

The following experimental examples are illustrative of the invention but not limitative of the scope thereof.

Example 1

Hydrated magnesium chloride (4 g), toluene (200 ml) and iso-butanol (12 g) were heated at 109°C for 24 hrs under continuous azeotropic distillation of water. The liquid was concentrated to separate a white crystalline solid (7.5 g) of magnesium chloride iso-butanolate, which was washed with toluene and then stirred with phthaloyl chloride (10 g) in toluene (200 ml) at 109°C for 12 hrs to give solid magnesium chloride ester complex precursor. The solid was filtered, washed with chlorobenzene and dried under a flow of nitrogen to give the precursor (3.5 g) having surface area 50 - 100 m²/g. The precursor was treated with titanium tetrachloride (10 ml) in chlorobenzene (50 ml) at 120°C for 2 hrs. The heterogeneous solid procatalyst thus obtained was filtered, washed with hexane and dried under a stream of nitrogen.

Example 2

Hydrated magnesium chloride (4 g), toluene (200 ml) and ethanol (5 g) were heated at 75°C for 24 hrs and then at 109°C for another 8 hrs under continuous azeotropic distillation of water. The liquid was concentrated to separate a white crystalline solid (7 g) of magnesium chloride ethanolate, which was washed with toluene and then stirred with benzoyl chloride (8.5 g) in toluene (200 ml) at 110°C for 12 hrs to give solid magnesium chloride ester complex precursor. The solid was filtered, washed with chlorobenzene and dried under a flow of nitrogen to give the precursor (5 g) having surface area 50 - 100 m²/g. The precursor was treated with titanium tetrachloride (50 ml) in chlorobenzene (50 ml) at 100°C for 2 hrs. The heterogeneous solid procatalyst thus obtained was filtered, washed with hexane and dried under a stream of nitrogen.

Example 3

Hydrated magnesium chloride (4 g), toluene (200 ml) and n-butanol (12 g) were heated at 109°C for 24 hrs under continuous azeotropic distillation of water. The reaction mixture was cooled to 60°C and benzoyl chloride (10 g) was added to the liquid and the mixture stirred magnetically for 12 hours at 110°C to separate out solid magnesium chloride ester complex precursor. Solid (5 g) which separated out was filtered, washed with chlorobenzene and dried under a flow of nitrogen to give the precursor (3.5 g) having surface area 50 - 100 m²/g. The precursor was treated with titanium tetrachloride (50 ml) in chlorobenzene (50 ml) at 100°C for 2 hrs. The

heterogeneous solid procatalyst thus obtained was filtered, washed with hexane and dried under a stream of nitrogen.

Example 4

5 Hydrated magnesium chloride (4 g), toluene (200 ml) and iso-butanol (12 g) were heated at 109°C for 24 hrs under continuous azeotropic distillation of water. The liquid was concentrated to separate a white crystalline solid (7.5 g) of magnesium chloride iso-butanolate. This was
10 washed with toluene and then stirred with benzoic anhydride (7.5 g) in toluene (200 ml) at 109°C for 12 hrs under continuous azeotropic distillation of water to give solid magnesium chloride ester complex precursor. The solid was filtered, washed with chlorobenzene and dried under a flow of nitrogen to give the precursor (5 g) having surface area 50 - 100 m²/g. The precursor was
15 treated with titanium tetrachloride (10 ml) in chlorobenzene (50 ml) at 100°C for 2 hrs. The heterogeneous solid procatalyst thus obtained was filtered, washed with hexane and dried under a stream of nitrogen.

Examples 5 to 8

20 Each of the heterogeneous solid procatalysts (0.1 g) of Examples 1 to 4 was mixed with triethyl aluminium cocatalyst (1.425 g) and p-ethoxy ethyl benzoate (0.61 g) as the selectivity control agent. The catalysts were mixed in the proportions such that aluminium : titanium : : 200 : 1. The mole ratio of the selectivity control agent to the titanium was 50 : 1. The catalysts
25 were employed to polymerise propylene in a slurry phase process with hexane

as the diluent under a constant pressure of 5 kg for 1hr at 70°C, followed by addition of 50 mmol of hydrogen to terminate the polymerisation.

Examples 9 to 12

5 The procedure of Examples 5 to 8 were repeated using dicyclohexyl dimethoxy silane (0.15 g) as the selectivity control agent. The mole ratio of the selectivity control agent to the titanium was 10 : 1.

10 In all the polymerisations, the activity of the catalysts were 3 - 7 kg of polymer/g of catalyst/hr and the polymers formed had an isotacticity index not less than 95%.

CLAIMS

1) A lower α -alkene polymerisation heterogeneous solid
catalyst comprising:

A) a hydrated magnesium chloride derived procatalyst comprising a titanium tetrahalide supported on a magnesium chloride ester complex precursor, wherein the internal electron donor ester component of the precursor is generated insitu by reaction of a magnesium chloride alcoholate with an activated carbonyl compound in the mole ratio 0.5 - 1 : 10 - 20; wherein the magnesium chloride alcoholate is formed of hydrated magnesium chloride and an aliphatic alcohol in the mole ratio of 0.5 - 1 : 10 - 20;

B) a cocatalyst comprising an organoaluminium compound, the mole ratio of the aluminium to the titanium being 10 - 300 : 1; and

C) a selectivity control agent comprising an ester or ether in the mole ratio 10 - 100 : 1 with respect to the titanium.

2) A catalyst as claimed in claim 1, wherein the titanium tetrahalide is titanium tetrachloride.

3) A catalyst as claimed in claim 1 or 2, wherein the aliphatic alcohol is ethanol, n-butanol or iso-butanol.

4) A catalyst as claimed in any one of claims 1 to 3, wherein the mole ratio of the hydrated magnesium chloride to the aliphatic alcohol is 1 : 10.

5) A catalyst as claimed in any one of claims 1 to 4, wherein the activated carbonyl compound is an acid halide.

6) A catalyst as claimed in claim 5, wherein the acid halide is benzoyl chloride or phthaloyl chloride.

7) A catalyst as claimed in any one of claims 1 to 4, wherein the activated carbonyl compound is an acid anhydride.

8) A catalyst as claimed in claim 7, wherein the acid anhydride is benzoic anhydride or phthalic anhydride.

9) A process for the preparation of a lower α -alkene polymerisation heterogeneous solid catalyst comprising mixing a hydrated magnesium chloride derived procatalyst, a cocatalyst comprising an organoaluminium compound and a selectivity control agent comprising an ester or ether, wherein the procatalyst is obtained by:

i) refluxing hydrated magnesium chloride with an aliphatic alcohol in the mole ratio 0.5 - 1 : 10 - 20 in a hydrocarbon and/or halohydrocarbon solvent followed by dehydration of the reaction mixture;

ii) reaction of the resulting magnesium chloride alcoholate with an activated carbonyl compound in the presence of a hydrocarbon and/or halohydrocarbon solvent in the mole ratio 0.5 - 1 : 10 - 20 at 30 - 160°C optionally followed by dehydration of the reaction mixture;

iii) reaction of the resulting magnesium chloride ester complex precursor comprising the internal electron donor ester component generated insitu, with a titanium tetrahalide optionally in the presence of a hydrocarbon and/or halohydrocarbon solvent at 30 - 130°C followed by isolating the resulting procatalyst; the mole ratio of the aluminium to the titanium being 10 - 300 : 1 and that of the selectivity control agent to the titanium being 10 - 100 : 1.

10) A process as claimed in claim 9, wherein the aliphatic alcohol is ethanol, n-butanol or iso-butanol.

11) A process as claimed in claim 9 or 10, wherein the mole ratio of the hydrated magnesium chloride to the aliphatic alcohol is 1 : 10.

12) A process as claimed in any one of claims 9 to 11, wherein the halohydrocarbon is chlorobenzene.

13) A process as claimed in any one of claims 9 to 12, wherein the hydrocarbon is toluene.

14) A process as claimed in any one of claims 9 to 13, wherein the reaction of the magnesium chloride alcoholate with the activated carbonyl compound is carried out *insitu*.

5 15) A process as claimed in any one of claims 9 to 14, wherein the reaction of the magnesium chloride alcoholate with the activated carbonyl compound is carried out after isolation of the magnesium chloride alcoholate.

10 16) A process as claimed in any one of claims 9 to 15, wherein the dehydration of the reaction mixture is carried out by azeotropic distillation.

17) A process as claimed in any one of claims 9 to 16, wherein the activated carbonyl compound is an acid halide.

15 18) A process as claimed in claim 17, wherein the acid halide is benzoyl chloride or phthaloyl chloride.

19) A process as claimed in any one of claims 9 to 16, wherein the activated carbonyl compound is an acid anhydride.

20 20) A process as claimed in claim 19, wherein the acid anhydride is benzoic anhydride or phthalic anhydride.

21) A process as claimed in any one of claims 9 to 20, wherein the reaction of the magnesium chloride alcoholate and the activated carbonyl compound is carried out at 100 - 110°C.

25

22) A process as claimed in any one of claims 9 to 21, wherein the mole ratio of the magnesium chloride alcoholate to the activated carbonyl compound is 0.5 : 10.

23) A process as claimed in any one of claims 9 to 22, wherein the titanium tetrahalide is titanium tetrachloride.

24) A process as claimed in any one of claims 9 to 23, wherein the reaction of the precursor with the titanium tetrahalide is carried out at 90 - 120°C.

25) A process as claimed in any one of claims 9 to 24, wherein the procatalyst is isolated by filtration.

26) A process for the preparation of a lower α -alkene polymerisation heterogeneous solid catalyst substantially as herein described particularly with reference to Examples 1 to 4.

27) A process for a lower α -alkene polymerisation comprising reacting under polymerisation conditions a lower α -alkene with a heterogeneous solid catalyst comprising:

A) a hydrated magnesium chloride derived procatalyst comprising a titanium tetrahalide supported on a magnesium chloride ester complex precursor, wherein the internal electron donor ester component of

the precursor is generated insitu by reaction of a magnesium chloride alcoholate with an activated carbonyl compound in the mole ratio 0.5 - 1 : 10 - 20; wherein the magnesium chloride alcoholate is formed of hydrated magnesium chloride and an aliphatic alcohol in the mole ratio of 0.5 - 1 : 10 - 20;

B) a cocatalyst comprising an organoaluminium compound, the mole ratio of the aluminium to the titanium being 10 - 300 : 1; and

C) a selectivity control agent comprising an ester or ether in the mole ratio 10 - 100 : 1 with respect to the titanium.

28) A process as claimed in claim 27, wherein the titanium tetrahalide is titanium tetrachloride.

29) A process as claimed in claim 27 or 28, wherein the aliphatic alcohol is ethanol, n-butanol or iso-butanol.

30) A process as claimed in any one of claims 27 to 29, wherein the mole ratio of the hydrated magnesium chloride to the aliphatic alcohol is 1 : 10.

31) A process as claimed in any one of claims 27 to 30, wherein the activated carbonyl compound is an acid halide.

32) A process as claimed in claim 31, wherein the acid halide is benzoyl chloride or phthaloyl chloride.

33) A process as claimed in any one of claims 27 to 30,
5 wherein the activated carbonyl compound is an acid anhydride.

34) A process as claimed in claim 33, wherein the acid anhydride is benzoic anhydride or phthalic anhydride.

10 35) A process for a lower α -alkene polymerisation substantially as herein described particularly with reference to Examples 5 to 12.

INTERNATIONAL SEARCH REPORT

International application No.
PCT/IN 00/00114

CLASSIFICATION OF SUBJECT MATTER

IPC⁷: C08F 4/654, C08F 10/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC⁷: B01J, C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPODOC, WPI, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4853444 A (INKROTT et al) 1 August 1989 (01.08.89) claims 1-7; example.	1-35
A	US 4761461 A (JAGGARD et al.) 2 August 1988 (02.08.88) example 1; column 5, lines 1-5.	1-35
A	EP 0360491 A2 (MITSUI PETROCHEMICAL INDUSTRIES, LTD.) 28 March 1990 (28.03.90) example 1; claims 1-10.	1-35
A	WO 90/09402 A1 (NESTE OY) 23 August 1990 (23.08.90) claims 1&3; page 13, line 25 - page 15, line 25.	1-35
A	WO 92/19658 A1 (NESTE OY) 12 November 1992 (12.11.92) amended claims 1,4,5,9&13; page 5, lines 26-32.	1-35
A	US 5234879 A (GAROFF et al.) 10 August 1993 (10.08.93) claims 1-14; column 4, line 34 - column 5, line 36.	1-35

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

„A“ document defining the general state of the art which is not considered to be of particular relevance

„E“ earlier application or patent but published on or after the international filing date

„L“ document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

„O“ document referring to an oral disclosure, use, exhibition or other means

„P“ document published prior to the international filing date but later than the priority date claimed

„T“ later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

„X“ document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

„Y“ document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

„&“ document member of the same patent family

Date of the actual completion of the international search

8 March 2001 (08.03.2001)

Date of mailing of the international search report

11 April 2001 (11.04.2001)

Name and mailing address of the ISA/AT

Austrian Patent Office

Kohlmarkt 8-10; A-1014 Vienna

Facsimile No. 1/53424/535

Authorized officer

PUSTERER

Telephone No. 1/53424/311

INTERNATIONAL SEARCH REPORT

International application No.

PCT/IN 00/00114

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0683175 A2 (MITSUI PETROCHEMICAL INDUSTRIES, LTD.) 22 November 1995 (22.11.95) examples 1-4.	1-35
A	US 5015612 A (KIOKA et al.) 14 May 1991 (14.05.91) claim 1; examples 1-7.	1-35
A	US 4401589 A (KIOKA et al.) 30 August 1983 (30.08.83) examples 1-19.	1-35
A	US 5731393 A (KOJOH et al.) 24 March 1998 (24.03.98) examples 1-4.	1-35
A	US 4801672 A (KOHYAMA et al.) 31 January 1989 (31.01.89) examples 1-7. -----	1-35

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/IN 00/00114

Patent document cited in search report			Publication date	Patent family member(s)			Publication date
EP	A2	360491	28-03-1990	AT	E	99336	15-01-1994
EP	A3	360491	05-06-1991	CA	A1	1334841	21-03-1995
EP	B1	360491	29-12-1993	CN	A	1042156	16-05-1990
				CN	B	1021229	16-06-1993
				DE	C0	68911812	10-02-1994
				DE	T2	68911812	14-04-1994
				ES	T3	2062025	16-12-1994
				JP	A2	2077407	16-03-1990
				JP	B2	2677395	17-11-1997
				KR	B1	9301064	15-02-1993
				US	A	4990477	05-02-1991
				US	A	5247031	21-09-1993
				JP	A2	2167312	27-06-1990
				JP	B2	2795476	10-09-1998
EP	A2	683175	22-11-1995	CA	AA	2149729	20-11-1995
EP	A3	683175	22-01-1997	CN	A	1112940	06-12-1995
EP	B1	683175	26-08-1998	DE	C0	69504237	01-10-1998
				DE	T2	69504237	29-04-1999
				HK	A1	1003713	17-03-2000
				JP	A2	8034813	06-02-1996
				US	A	6034189	07-03-2000
US	A	4401589	30-08-1983	AT	A	3230/80	15-11-1981
				AT	B	367433	12-07-1982
				AU	A1	59352/80	08-01-1981
				AU	B2	537328	21-06-1984
				BE	A1	883858	17-12-1980
				BR	A	8003776	13-01-1981
				CA	A1	1154197	20-09-1983
				DD	C	151630	28-10-1981
				DE	A1	3022738	22-01-1981
				DE	C2	3022738	04-09-1986
				DK	A	2579/80	19-12-1980
				DK	B	158585	11-06-1990
				DK	C	158585	05-11-1990
				FI	A	801946	19-12-1980
				FI	B	68063	29-03-1985
				FI	C	68063	10-07-1985
				FR	A1	2459252	09-01-1981
				FR	B1	2459252	23-08-1985
				GB	A1	2052534	28-01-1981
				GB	B2	2052534	29-06-1983
				HU	B	195841	28-07-1988
				IN	A	151948	10-09-1983
				IT	A0	8022870	18-06-1980
				IT	A	1141003	01-10-1986
				JP	A2	56000811	07-01-1981
				JP	B4	63054004	26-10-1988
				NL	A	8003502	22-12-1980
				NL	B	183765	16-08-1988
				NL	C	183765	16-01-1989
				NO	A	801807	19-12-1980
				NO	B	157298	16-11-1987
				NO	C	157298	24-02-1988
				PH	A	16388	19-09-1983
				PL	A1	225031	19-06-1981
				RO	P	80874	21-06-1984
				SE	A	8004464	06-02-1981
				SE	B	449615	11-05-1987
				SE	C	449615	20-08-1987
				SG	A	755/85	21-11-1986
				US	A	4330649	18-05-1982
				JP	A2	63264609	01-11-1988
				JP	B4	5015722	02-03-1993
US	A	4761461	02-08-1988	AT	E	59189	15-01-1991
				DE	A1	3540699	27-05-1987
				DE	C0	3676283	31-01-1991
				EP	A1	226003	24-06-1987
				EP	B1	226003	19-12-1990
				JP	A2	62119208	30-05-1987
				JP	B4	7025834	22-03-1995
				ZA	A	8608646	27-07-1988
US	A	4801672	31-01-1989	CA	A1	1262997	14-11-1989
				DE	C0	3579428	04-10-1990
				EP	A2	186287	02-07-1986
				EP	A3	186287	13-05-1987

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/IN 00/00114

Patent document cited in search report			Publication date	Patent family member(s)	Publication date
US	A	4853444	01-08-1989	EP B1 186287	29-08-1990
				JP A2 61108614	27-05-1986
				JP B4 3039525	14-06-1991
				CA A1 1214312	25-11-1986
				EP A1 143339	05-06-1985
				EP B1 143339	04-09-1991
				ES A1 537107	16-12-1985
				ES A5 537107	16-01-1986
				ES A1 8603514	16-04-1986
				JP A2 60112614	19-06-1985
				JP B4 3062167	25-09-1991
				NO A 844184	29-04-1985
				NO B 166718	21-05-1991
				NO C 166718	28-08-1991
				US A 4520121	28-05-1985
US	A	5015612	14-05-1991	AT E 101400	15-02-1994
				CA A1 1336594	08-08-1995
				CN A 1041162	11-04-1990
				CN A 1084180	23-03-1994
				CN A 1084186	23-03-1994
				CN A 1084187	23-03-1994
				CN A 1085225	13-04-1994
				CN A 1097769	25-01-1995
				CN A 1101353	12-04-1995
				CN B 1033590	18-12-1996
				CN B 1043649	16-06-1999
				CN B 1043899	30-06-1999
				CN B 1044125	14-07-1999
				CN B 1044126	14-07-1999
				CN B 1044373	28-07-1999
				DE C0 68912996	24-03-1994
				DE T2 68912996	21-07-1994
				EP A2 360497	28-03-1990
				EP A3 360497	31-07-1991
				EP B1 360497	09-02-1994
				KR B1 9207040	24-08-1992
				JP A2 2191608	27-07-1990
				JP B2 2790870	27-08-1998
				JP A2 3163110	15-07-1991
				JP B2 2788012	20-08-1998
US	A	5234879	10-08-1993	AT E 143675	15-10-1996
				DE C0 69122483	07-11-1996
				DE T2 69122483	06-02-1997
				EP A2 491566	24-06-1992
				EP A3 491566	16-09-1992
				EP B1 491566	02-10-1996
				ES T3 2094798	01-02-1997
				FI A0 906282	19-12-1990
				FI A 906282	20-06-1992
				FI B 86866	15-07-1992
				FI C 86866	26-10-1992
				JP A2 4296305	20-10-1992
				JP B2 2559084	27-11-1996
				NO A0 915000	18-12-1991
				NO A 915000	22-06-1992
				NO B 178731	12-02-1996
				NO C 178731	22-05-1996
US	A	5731393	24-03-1998	CA AA 2142753	19-08-1995
				CA C 2142753	29-09-1998
				DE C0 69502315	10-06-1998
				DE T2 69502315	05-11-1998
				EP A1 669347	30-08-1995
				EP B1 669347	06-05-1998
				JP A2 7228629	29-08-1995
				KR B1 178075	15-05-1999
WO	A1	9009402	23-08-1990	CA AA 2047712	17-08-1990
				EP A1 451214	16-10-1991
				FI A0 890765	16-02-1989
				FI A 890765	17-08-1990
				FI B 83332	15-03-1991
				FI C 83332	25-06-1991
				JP T2 4504865	27-08-1992
				NO A 913100	08-08-1991
				NO A0 913100	08-08-1991
				CA AA 2056531	20-06-1992

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No.

PCT/IN 00/00114

Patent document cited in search report			Publication date	Patent family member(s)			Publication date
WO	A1	9219658	12-11-1992	CA	AA	2102306	10-11-1992
				DE	C0	69220058	03-07-1997
				DE	T2	69220058	02-10-1997
				EP	A1	586390	16-03-1994
				EP	B1	586390	28-05-1997
				FI	A0	912263	09-05-1991
				FI	B	88048	15-12-1992
				FI	C	88048	25-03-1993
				NO	A	934041	08-11-1993
				NO	A0	934041	08-11-1993
				US	A	5767215	16-06-1998